

Hendrick

ARCHITECTURAL

Perforated Corrugated Color Chart

877-840-0881

www.hendrickarch.com

arch@hendrickcorp.com

Carbondale, PA | Elgin, IL | Owensboro, KY

Standard Colors (PVDF Finish)


PVDF resin based coatings provide high-performance durability for exterior and interior applications. These coatings are designed to resist fading, chalking, and abrasion. Meets the requirement of AAMA 2605-13 and AAMA 620-02.



Black (02)




Patina Green (12)




Concord Cream (05)



Charcoal Grey (62)




Classic Bronze (01)



Chocolate Brown (04)



Almond (36)




Slate Grey (20)



Medium Bronze (03)



Boysenberry (25)



Sandstone (06)



Dove Grey (13)




Hartford Green (27)



Redwood (07)



Regal Blue (18)



Ascot White (10)




Forest Green (11)



Mission Red (08)



Slate Blue (21)



Bone White (26)



Teal (19)



Sierra Tan (09)



Siam Blue (14)



Hemlock Green (30)



Rawhide (15)



Rocky Grey (16)

Premium Finish (PVDF Finish)

PVDF resin based coatings, as noted above, with premium pigmentation to obtain metallic or deep color for desired aesthetics.



Antique Patina (24)



Champagne (31)



Coppertone (23)



Titanium (35)



Silversmith (28)



Brite Red (17)



Clear Anodized (70)



Dark Bronze Anodized (71)

ALL colors & finishes available in:

.032" aluminum

.040" aluminum

.050" aluminum

Please inquire about custom colors & materials.



Hendrick

ARCHITECTURAL

Perforated Corrugated Color Reference Guide

877-840-0881

www.hendrickarch.com

arch@hendrickcorp.com

Carbondale, PA | Elgin, IL | Owensboro, KY

STANDARD COLORS	Color Number	Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)
Classic Bronze	01	0.09	0.87	3
Black	02	0.05	0.88	-1
Medium Bronze	03	0.32	0.85	33
Chocolate Brown	04	0.27	0.85	25
Concord Cream	05	0.65	0.85	78
Sandstone	06	0.57	0.85	66
Redwood	07	0.29	0.86	29
Mission Red	08	0.44	0.86	48
Sierra Tan	09	0.46	0.85	51
Ascot White	10	0.67	0.85	80
Forest Green	11	0.25	0.84	23
Patina Green	12	0.43	0.85	47
Dove Grey	13	0.48	0.85	54
Siam Blue	14	0.34	0.85	35
Rawhide	15	0.55	0.85	64
Rocky Grey	16	0.28	0.86	28
Regal Blue	18	0.25	0.84	23
Teal	19	0.30	0.85	30
Slate Grey	20	0.39	0.85	42
Slate Blue	21	0.31	0.86	31
Boysenberry	25	0.28	0.85	27
Bone White	26	0.73	0.85	89
Hartford Green	27	0.25	0.85	23
Hemlock Green	30	0.30	0.86	30
Almond	36	0.62	0.87	74
Charcoal Grey	62	0.28	0.86	27
PREMIUM COLORS	Color Number	Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)
Brite Red	17	0.37	0.86	39
Coppertone	23	0.50	0.86	57
Antique Patina	24	0.26	0.86	25
Silversmith	28	0.47	0.81	51
Champagne	31	0.55	0.79	62
Titanium	35	0.51	0.87	59
Clear Anodized	70	0.77	0.70	92
Dark Bronze Anodized	71	0.15	0.77	6